

Technical data sheet

Austrotherm EPS[®] FF

Description:	Expanded polystyrene boards for insulation in construction																																																																																
Application:	For thermal insulation of external walls in a combined thermal insulation system (WDVS) according to BDS EN 13163:2012+A2:2017.																																																																																
Format:	Plates with a length of 1000 mm , a width of 500 mm , thicknesses from 20 to 400 mm Edge shape: Straight edge (GK).																																																																																
Quantity in package:	<table border="1"> <thead> <tr> <th>Thickness (mm)</th> <th>Length x width (mm)</th> <th>Number of plates</th> <th>Area (m²)</th> <th>R_D m² K¹/W</th> </tr> </thead> <tbody> <tr><td>20</td><td>1000x500</td><td>24</td><td>12.0</td><td>0.50</td></tr> <tr><td>30</td><td>1000x500</td><td>16</td><td>8.0</td><td>0.75</td></tr> <tr><td>40</td><td>1000x500</td><td>12</td><td>6.0</td><td>1.05</td></tr> <tr><td>50</td><td>1000x500</td><td>10</td><td>5.0</td><td>1.30</td></tr> <tr><td>60</td><td>1000x500</td><td>8</td><td>4.0</td><td>1.55</td></tr> <tr><td>70</td><td>1000x500</td><td>7</td><td>3.5</td><td>1.80</td></tr> <tr><td>80</td><td>1000x500</td><td>6</td><td>3.0</td><td>2.10</td></tr> <tr><td>90</td><td>1000x500</td><td>5</td><td>2.5</td><td>2.35</td></tr> <tr><td>100</td><td>1000x500</td><td>5</td><td>2.5</td><td>2.60</td></tr> <tr><td>120</td><td>1000x500</td><td>4</td><td>2.0</td><td>3.15</td></tr> <tr><td>140</td><td>1000x500</td><td>4</td><td>2.0</td><td>3.65</td></tr> <tr><td>150</td><td>1000x500</td><td>3</td><td>1.5</td><td>3.90</td></tr> <tr><td>160</td><td>1000x500</td><td>3</td><td>1.5</td><td>4.20</td></tr> <tr><td>180</td><td>1000x500</td><td>3</td><td>1.5</td><td>4.70</td></tr> <tr><td>200</td><td>1000x500</td><td>2</td><td>1.0</td><td>5.25</td></tr> </tbody> </table>	Thickness (mm)	Length x width (mm)	Number of plates	Area (m ²)	R _D m ² K ¹ /W	20	1000x500	24	12.0	0.50	30	1000x500	16	8.0	0.75	40	1000x500	12	6.0	1.05	50	1000x500	10	5.0	1.30	60	1000x500	8	4.0	1.55	70	1000x500	7	3.5	1.80	80	1000x500	6	3.0	2.10	90	1000x500	5	2.5	2.35	100	1000x500	5	2.5	2.60	120	1000x500	4	2.0	3.15	140	1000x500	4	2.0	3.65	150	1000x500	3	1.5	3.90	160	1000x500	3	1.5	4.20	180	1000x500	3	1.5	4.70	200	1000x500	2	1.0	5.25
Thickness (mm)	Length x width (mm)	Number of plates	Area (m ²)	R _D m ² K ¹ /W																																																																													
20	1000x500	24	12.0	0.50																																																																													
30	1000x500	16	8.0	0.75																																																																													
40	1000x500	12	6.0	1.05																																																																													
50	1000x500	10	5.0	1.30																																																																													
60	1000x500	8	4.0	1.55																																																																													
70	1000x500	7	3.5	1.80																																																																													
80	1000x500	6	3.0	2.10																																																																													
90	1000x500	5	2.5	2.35																																																																													
100	1000x500	5	2.5	2.60																																																																													
120	1000x500	4	2.0	3.15																																																																													
140	1000x500	4	2.0	3.65																																																																													
150	1000x500	3	1.5	3.90																																																																													
160	1000x500	3	1.5	4.20																																																																													
180	1000x500	3	1.5	4.70																																																																													
200	1000x500	2	1.0	5.25																																																																													
Product type:	Other thicknesses and plate formats on request. Expanded polystyrene (EPS) according to EN 13163																																																																																
Designation:	EPS[®] FF marking on the short side of the package																																																																																
Designation code:	EPS-EN 13163-T1-L2-W2-Sb2-P5-DS(N)2-DS(70,-)1-BS125-CS(10)70-TR130-WL(T)2-MU(20-40)																																																																																
Technical data:	<table border="0"> <tr> <td>Thermal conductivity λ :</td> <td>≤ 0.038 W/mK</td> </tr> <tr> <td>Compressive strength CS :</td> <td>≥ 70 kPa</td> </tr> <tr> <td>Bending strength BS :</td> <td>≥ 125 kPa</td> </tr> <tr> <td>Tensile strength TR t :</td> <td>≥ 130 kPa</td> </tr> <tr> <td>Water absorption during prolonged full immersion:</td> <td>≤ 2 % by volume</td> </tr> <tr> <td>Water vapor diffusion resistance number μ:</td> <td>20-40</td> </tr> <tr> <td>Reaction to fire class:</td> <td>E</td> </tr> </table>	Thermal conductivity λ :	≤ 0.038 W/mK	Compressive strength CS :	≥ 70 kPa	Bending strength BS :	≥ 125 kPa	Tensile strength TR t :	≥ 130 kPa	Water absorption during prolonged full immersion:	≤ 2 % by volume	Water vapor diffusion resistance number μ :	20-40	Reaction to fire class:	E																																																																		
Thermal conductivity λ :	≤ 0.038 W/mK																																																																																
Compressive strength CS :	≥ 70 kPa																																																																																
Bending strength BS :	≥ 125 kPa																																																																																
Tensile strength TR t :	≥ 130 kPa																																																																																
Water absorption during prolonged full immersion:	≤ 2 % by volume																																																																																
Water vapor diffusion resistance number μ :	20-40																																																																																
Reaction to fire class:	E																																																																																
Application temp.:	Up to 85°C.																																																																																
Processing:	According to the operating instructions and requirements of the manufacturer of the components of the combined thermal insulation system.																																																																																

Austrotherm EPS[®] does not contain chlorofluorocarbons (CFCs), HFCs, HFCS, or HBCD .

Last edited : 11/20 24

