

Technical data sheet

Austrotherm EPS® 120

Description:	Expanded polystyrene boards for insulation with high compressive loads in construction																																																																																				
Application:	For thermal insulation of flat roofs, under screed, wherever high compressive strength is required structurally																																																																																				
Format:	Plates with a length of 1000 mm , a width of 500 mm , thicknesses from 20 to 200 mm Edge shape: Straight edge (GK)																																																																																				
Quantity in package:	<table><tr><th>Thickness (mm)</th><th>Length x width (mm)</th><th>Number of plates</th><th>Area (m²)</th><th>R_D m²K/W</th></tr><tr><td>20</td><td>1000 x 500</td><td>30</td><td>15</td><td>0,55</td></tr><tr><td>30</td><td>1000 x 500</td><td>20</td><td>10</td><td>0,85</td></tr><tr><td>40</td><td>1000 x 500</td><td>15</td><td>7,5</td><td>1,15</td></tr><tr><td>50</td><td>1000 x 500</td><td>12</td><td>6</td><td>1,45</td></tr><tr><td>60</td><td>1000 x 500</td><td>10</td><td>5</td><td>1,75</td></tr><tr><td>70</td><td>1000 x 500</td><td>8</td><td>4</td><td>2,05</td></tr><tr><td>80</td><td>1000 x 500</td><td>7</td><td>3,5</td><td>2,35</td></tr><tr><td>90</td><td>1000 x 500</td><td>6</td><td>3</td><td>2,60</td></tr><tr><td>100</td><td>1000 x 500</td><td>6</td><td>3</td><td>2,90</td></tr><tr><td>120</td><td>1000 x 500</td><td>5</td><td>2,5</td><td>3,50</td></tr><tr><td>140</td><td>1000 x 500</td><td>4</td><td>2</td><td>4,10</td></tr><tr><td>150</td><td>1000 x 500</td><td>4</td><td>2</td><td>4,40</td></tr><tr><td>160</td><td>1000 x 500</td><td>3</td><td>1,5</td><td>4,70</td></tr><tr><td>180</td><td>1000 x 500</td><td>3</td><td>1,5</td><td>5,25</td></tr><tr><td>200</td><td>1000 x 500</td><td>3</td><td>1,5</td><td>5,85</td></tr></table> Other thicknesses, slab formats – upon request.					Thickness (mm)	Length x width (mm)	Number of plates	Area (m²)	R _D m²K/W	20	1000 x 500	30	15	0,55	30	1000 x 500	20	10	0,85	40	1000 x 500	15	7,5	1,15	50	1000 x 500	12	6	1,45	60	1000 x 500	10	5	1,75	70	1000 x 500	8	4	2,05	80	1000 x 500	7	3,5	2,35	90	1000 x 500	6	3	2,60	100	1000 x 500	6	3	2,90	120	1000 x 500	5	2,5	3,50	140	1000 x 500	4	2	4,10	150	1000 x 500	4	2	4,40	160	1000 x 500	3	1,5	4,70	180	1000 x 500	3	1,5	5,25	200	1000 x 500	3	1,5	5,85
Thickness (mm)	Length x width (mm)	Number of plates	Area (m²)	R _D m²K/W																																																																																	
20	1000 x 500	30	15	0,55																																																																																	
30	1000 x 500	20	10	0,85																																																																																	
40	1000 x 500	15	7,5	1,15																																																																																	
50	1000 x 500	12	6	1,45																																																																																	
60	1000 x 500	10	5	1,75																																																																																	
70	1000 x 500	8	4	2,05																																																																																	
80	1000 x 500	7	3,5	2,35																																																																																	
90	1000 x 500	6	3	2,60																																																																																	
100	1000 x 500	6	3	2,90																																																																																	
120	1000 x 500	5	2,5	3,50																																																																																	
140	1000 x 500	4	2	4,10																																																																																	
150	1000 x 500	4	2	4,40																																																																																	
160	1000 x 500	3	1,5	4,70																																																																																	
180	1000 x 500	3	1,5	5,25																																																																																	
200	1000 x 500	3	1,5	5,85																																																																																	
Product type:	Expanded polystyrene (EPS) according to Harmonized Standard EN 13163:2012+A2:2016; National Reference No. BDS EN 13163:2012+A2:2017																																																																																				
Designation:	EPS® 120 marking on the short side of the package																																																																																				
Designation code:	EPS-EN 13163-T1-L2-W2-Sb2-P5-DS(N)2-DS(70,-)1-BS250-CS(10)120-TR220-WL(T)2-MU(30÷70)																																																																																				
Technical data:	<table><tr><td>Thermal conductivity λ:</td><td>≤ 0,034 W/mK</td></tr><tr><td>Compressive strength (CS):</td><td>≥ 120 kPa</td></tr><tr><td>Bending strength (BS):</td><td>≥ 250 kPa</td></tr><tr><td>Tensile strength (TR):</td><td>≥ 220 kPa</td></tr><tr><td>Water absorption during prolonged full immersion:</td><td>≤ 2% by volume</td></tr><tr><td>Water vapor diffusion resistance number μ:</td><td>30-70</td></tr><tr><td>Reaction to fire class:</td><td>E</td></tr></table>					Thermal conductivity λ:	≤ 0,034 W/mK	Compressive strength (CS):	≥ 120 kPa	Bending strength (BS):	≥ 250 kPa	Tensile strength (TR):	≥ 220 kPa	Water absorption during prolonged full immersion:	≤ 2% by volume	Water vapor diffusion resistance number μ:	30-70	Reaction to fire class:	E																																																																		
Thermal conductivity λ:	≤ 0,034 W/mK																																																																																				
Compressive strength (CS):	≥ 120 kPa																																																																																				
Bending strength (BS):	≥ 250 kPa																																																																																				
Tensile strength (TR):	≥ 220 kPa																																																																																				
Water absorption during prolonged full immersion:	≤ 2% by volume																																																																																				
Water vapor diffusion resistance number μ:	30-70																																																																																				
Reaction to fire class:	E																																																																																				
Application temp.:	Up to 85°C.																																																																																				
Processing:	According to work instructions and construction safety instructions.																																																																																				

Austrotherm EPS® does not contain chlorofluorocarbons (CFCs), HFCs, HFCS, or HBCD.

Last edited: 08/2026